

LOCTITE EDAG 503 62% E&C

June 2015

PRODUCT DESCRIPTION

LOCTITE EDAG 503 62% E&C provides the following product characteristics:

Technology	Fluoroelastomer
Appearance	Silver
Filler Type	Silver
Carrier Type	Methyl Isobutyl Ketone (MIBK)
Solvent	Butyl Acetate, MEK or MIBK
Operating Temperature	275 °C
Product Benefits	<ul style="list-style-type: none"> • Conductive • General purpose • Flexible • High temperature performance • Dries at room temperature • Resistant to acids and alkali • Good adhesion • Humidity resistant • One component • Process ease
Cure	Air dry
Application	Conductive coating
Typical Assembly Applications	<ul style="list-style-type: none"> • Electrical terminations • EMI shielding • Static bleeds • Fabric coating • Painted antennas • Printed circuitry • Component manufacture • Microwave strip and control lines • Heating elements • Cable coatings • Conductive contact material • Tantalum capacitors

LOCTITE EDAG 503 62% E&C is a general purpose coating suitable for direct application to most substrates including plastics and elastomers. It is designed to exhibit good resistance to ultraviolet radiation, oxidation and corona.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Weight Solids, %	62
Viscosity, Brookfield - LVT, mPa·s (cP):	
Spindle 2, speed 12 rpm, Shake 5 minutes	1,700
Density, kg/l	1.75
Theoretical coverage, m ² /kg:	
@ 25µm	4.0
Shelf Life, from date of qualification in original seal, years	2
Flash Point °C	20

TYPICAL DRYING PERFORMANCE

Recommended Drying Conditions

15 minutes @ 150°C or
 1 hour @ 25°C

Percent Volatiles

VOC, g/l 675

Allow LOCTITE EDAG 503 62% E&C to dry at above temperatures prior to soldering.

The above drying profile is a guideline recommendation. Conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer drying equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Electrical Properties

Volume Resistivity, Ω·cm 127
 Sheet Resistivity, ohms/sq:
 @ 1 mil dry coating thickness 0.05

Specific resistance tests should be conducted prior to design.

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

1. Do not freeze
2. Keep product container tightly closed when not in use
3. Keep away from heat, sparks and open flame
4. Protect material from direct sunlight
5. Ground and bond containers when transferring materials
6. **Surface Preparation**
 - Surface to be coated must be dry and free on contaminants such as oil or chemical residues.
 - Porcelains and other smooth substrates can be wiped with solvents, such as acetone, and air dried.
 - Porous substrates, including materials coated with Aquadag E™, should be heated sufficiently after the solvent wipe to drive off any entrapped contaminants, solvents and moisture.
7. **Mixing/Dilution**
 - Before use, the material should be mixed thoroughly using a mechanical stirrer or paint shaker until it is of uniform consistency. Check to see that no sediment remains in the bottom of the container..
 - LOCTITE EDAG 503 62% E&C is supplied ready for brushing and roller applications.
 - One or two parts of MEK by volume can be added to one part of the product for spraying, dip coating or impregnation. Use care when dipping plastics that can be affected by MEK.
 - Pour into suitable container for dilution (e.g., pressure pot, etc.).



8. Spray Application

- For small production work prototypes, a suction cup gun may be used, providing LOCTITE EDAG 503 62% E&C is thoroughly mixed prior to spray application.
- For intermediate production runs or many small parts, propeller-type attachments should be used on the suction gun to ensure coating uniformity.
- Full production is most efficiently handled with propeller agitated pressure pot systems.
- Handle LOCTITE EDAG 503 62% E&C as you would a quality automotive lacquer. Avoid dry spray as this will cause poor adhesion.
- To reduce overspray, use the minimum atomization pressure required for adequate coverage.
- Further dilution of LOCTITE EDAG 503 62% E&C may be desirable to improve product yield, since any overspray will contain less silver.

9. Soldering of Coatings

- Solder with a 60/40 resin core solder after pre-tinning at a lower temperature.
- A 20watt pencil tip soldering iron will provide best results.
- Dip soldering is best at a 195 to 210°C without a flux.
- When dip soldering, use a 2% silver, 60/38 solder.

Clean-up

To clean screen and equipment, use MEK

Storage

Store product in the unopened container in a cool dry well ventilated area. Storage information may be indicated on the product container labeling.

Optimal Storage: 5 to 20°C. Storage below 5°C or greater than 20°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Empty containers may retain hazardous properties.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} = \text{N/mm}^2$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product

can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2